


## PRODUCT DATA SHEET WINFAB 105SF-36/06/1.5

SUCCESS

**WINFAB 105SF-36/06/1.5** is a preassembled silt fence unit composed of **WINFAB 105SF** silt fence fabric as well as the components listed in the chart below.



			CALLED AND AND AND AND AND AND AND AND AND AN
ASSEMBLED UNIT PROPERTY	TEST METHOD	TYPICAL ENGLISH	TYPICAL METRIC
Post Size	Measured	1.5 X 1.5 X 48 in (2 in Nominal)	38.1 x 38.1 x 1,219.2 mm (50.8 mm Nominal)
Post Spacing	Measured	6 ft	1.83 m
Post Composition	-	Hardwood with Pencil Point	
Fabric Height	Measured	36 in	.914 m
Unit Length	Measured	100 ft	30.48 m

**WINFAB 105SF** is a silt fence fabric manufactured using high tenacity polypropylene yarns that are woven to form a dimensionally stable network, which allows the yarns to maintain their relative position. It resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals. It meets or exceeds the requirements of AASHTO M288 for unsupported silt fence and ASTM D6461 table 1.

PROPERTY	TEST METHOD	MARV ENGLISH	MARV METRIC
Tensile Strength (Grab)	ASTM D4632	125 x 124 lbs	556 x 551.6 N
Elongation (Grab)	ASTM D4632	15% x 15%	15% x 15%
Trapezoidal Tear Strength	ASTM D4533	65 x 65 lbs	289.1 x 289.1 N
CBR Puncture	ASTM D6241	325 lbs	1,445.7 N
UV Resistance (500 hrs)	ASTM D4355	70%	70%
Apparent Opening Size*	ASTM D4751	30 US Std. Sieve	0.60 mm
Permittivity	ASTM D4491	.1 sec <sup>-1</sup>	.1 sec <sup>-1</sup>
Water Flow Rate	ASTM D4491	8 gpm/ft²	326 lpm/m <sup>2</sup>

<sup>\*</sup>Maximum Average Roll Valve

**Disclaimer:** WINFAB assumes no liability for the completeness or accuracy of this information or the ultimate use of this information. WINFAB disclaims any and all implied, expressed, or statutory standards, guarantees, or warranties. This includes without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The end user assumes sole responsibility for the use of this information and product. The property values listed above are subject to change without notice.

© 2018 WINFAB

WINFAB | www.winfabusa.com 1 Nashville Mills Rd. Nashville GA 31639 Ph: (912) 534-5757 • Fax: (912) 534-5533



